



Handled by, department
Magnus Sturesson
Fire Technology
+46 10 516 55 70, magnus.sturesson@sp.se

Rev.date
2010-11-17

Armatec Environmental Ltd
P.O. Box 3046
New Plymouth
New Zealand

Fire Endurance Test of plastic pipe according to IMO Resolution A.753(18), Appendix 2

(3 appendices)

Products

According to the client:

Plastic pipe systems called "Whispa Pipe" and "Single layer FRP Pipe". The "Whispa Pipe" has a nominal outer diameter of 185 mm and a nominal inner diameter of 153 mm giving a wall thickness of 16 mm. The "Single layer FRP Pipe" has a nominal outer diameter of 165 mm and a nominal inner diameter of 153 mm giving a wall thickness of 6 mm. The nominal working pressure of the pipes are 1-3 bar.

Manufacturer

Armatec Environmental Ltd, New Plymouth, New Zealand.

Purpose of test

Basis for fire technical classification.

Sampling

The samples were delivered by the client. It is not known to SP, Fire Technology if the products received are representative of the mean production characteristics.

The samples were received September 29, 2010 at SP, Fire Technology.

Test Procedure

Test method for fire endurance testing of water-filled plastic piping (Level 3), IMO Resolution A.753(18), Appendix 2, clause 4.

SP Technical Research Institute of Sweden

Postal address
SP
Box 857
SE-501 15 BORÅS
Sweden

Office location
Västeråsen
Brinellgatan 4
Borås

Phone / Fax / E-mail
+46 10 516 50 00
+46 33 13 55 02
info@sp.se

This document may not be reproduced other than in full, except with the prior written approval of SP.

Test results

The test results are given in appendix 1 - 2. Photographs are given in appendix 3.

The tests were performed on material conditioned for more than 48 hours at 23 ± 2 °C and (50 ± 5) % relative humidity.

The test results relate only to the behaviour of the test specimens of a product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Criteria

To meet "Fire Endurance level 3" according to IMO Resolution A.753(18), clause 2.2.1.2.3 and Appendix 2, clause 4, no leakage from the sample(s) should occur except that slight weeping through the pipe wall may be accepted when tested during 30 minutes.

After termination of the burner regulation test, the test sample, together with fire-protective coating, if any, should be allowed to cool to ambient temperature and then tested to the rated pressure of the pipes as defined in paragraphs 2.1.2.2 and 2.1.3.2 of IMO Resolution A.753(18). The pressure should be held for a minimum of 15 minutes without significant leakages, i.e. not exceeding 0.2 l/min.

Assessment

The tested plastic piping systems called "Whispa Pipe" and "Single layer FRP Pipe" meet the criteria mentioned above and is evaluated up to the rated pressure of 3 bar.

SP Technical Research Institute of Sweden Fire Technology - Fire Dynamics



Magnus Sturesson
Technical Officer



Per Thureson
Technical Manager

Appendices

- 1 Test results, Whispa Pipe
- 2 Test results, Single layer FRP Pipe
- 3 Photographs